

Amercoat 880

DESCRIPTION

Glass flake additive

PRINCIPAL CHARACTERISTICS

- Provides mechanical film reinforcement
- Lowers film permeability
- Increases film build

COLOR AND GLOSS LEVEL

- white powder

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Shelf life	At least 60 months when stored cool and dry

INSTRUCTIONS FOR USE

1. Add slowly to products under mechanical agitation to avoid agglomeration of the glass flake.
2. Add Amercoat 880 to products as prescribed in the table below.
3. Application by airless spray will require a mastic gun with a 0.035" spray tip.
4. Be aware that addition of Amercoat 880 glass flake will slightly increase dry times at equal film thickness as compared to products without glass flake.

Addition Rates for specific products	
Product	Addition rate
Amerlock 2/400	1 gallon can per 2 mixed gallons; 3 gallon can per 5 mixed gallons
Amercoat 385	1 gallon can per 2 mixed gallons; Two 3-gallon cans per 10 mixed gallons
AMERCOAT 370	1 gallon can per 5 mixed gallons
Amercoat 240	2 gallon cans per 5 mixed gallons
Amercoat 91	1/2 of 1 gallon can per 1 mixed gallon ; One 3-gallon can per 5 mixed gallons



Amercoat 880

DISCLAIMER

- For professional use only. Not for household use

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

Product code	Description
AT880	Glass flake additive

Note: Available in 1-gallon cans (3.62 lbs) and 3-gallon cans (9.05 lbs)

