

# PITT-TECH® | 90-374 SERIES

## DESCRIPTION

One-component, int./ext gloss DTM Industrial enamel

## PRINCIPAL CHARACTERISTICS

- Waterborne acrylic enamel
- Ease of application, brush, roll, or spray
- Low odor, soap and water clean up
- Excellent gloss retention and weathering
- Self Priming in many applications
- Flash rust resistant
- Washable, scrub resistant

## COLOR AND GLOSS LEVEL

- White, black, safety colors, custom colors
- Gloss

Note: Certain colors, especially red, orange, and yellow may require additional coats for adequate hiding, especially if applied over primers with a significant color contrast

## BASIC DATA AT 68°F (20°C)

Data for product	
Number of components	One
Volume solids	37 ± 3%
VOC (Supplied)	max. 1.6 lb/US gal (approx. 192 g/l)
Temperature resistance (Continuous)	To 200°F (93°C)
Temperature resistance (Intermittent)	To 250°F (121°C)
Recommended dry film thickness	2.0 - 3.0 mils (50 - 75 µm) depending on system
Theoretical spreading rate	297 ft <sup>2</sup> /US gal for 2.0 mils (7.4 m <sup>2</sup> /l for 50 µm)
Shelf life	At least 36 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time
- Discoloration will occur at high temperatures



# PITT-TECH® | 90-374 SERIES

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is proportional to the degree of surface preparation. Refer to the application instructions for specific primers and intermediate coats for application and curing procedures. Ensure epoxies are free from amine blush prior to overcoating. All previous coats must dry and free of contaminants. Adhere to all minimum and maximum topcoat times for specific primers and intermediate coats. Aged epoxy coatings require abrading prior to applying the product. A test patch over unknown coatings is recommended.

---

### **Steel**

- Remove all rust, dirt, moisture, grease or other contaminants from the surface in accordance with SSPC SP-1
- Power tool clean in accordance with SSPC SP-3 or hand tool clean to SSPC SP-2 requirements. Alternately, abrasive blast to SSPC SP-7 requirements. Abrasive blasting to SSPC SP-6 or better is also allowable and will give the best possible system performance
- Note that a primer must be used on all bare metal substrates when using colors made from Midtone, Deeptone, and Deep Rustic bases

---

### **Non-ferrous metals and galvanizing**

- Remove oil or soap film with detergent or emulsion cleaner as per SSPC SP-1 and galvanizing requirements, then use a phosphatizing conversion coating
- Alternately, power tool clean to uniformly abrade the surface or lightly abrasive blast with a fine abrasive to produce a uniform and dense anchor profile of 1.0 – 2.0 mils (25 – 50 µm) in accordance with SSPC SP-16.
- Galvanizing that has had at least 12 months of exterior weathering may be coated after power washing to remove all contaminants and white rust
- Galvanized surfaces that have been passivated with a chromate treatment must be abrasive blasted. Coatings may not adhere to chromate sealed galvanizing if the chromates are not completely removed.

---

### **Concrete / Masonry**

- Clean concrete surface, abrasive blast per ASTM D4259 or acid-etch in accordance with ASTM D 4260
- Fill concrete voids with AMERCOAT 965 or AMERCOAT 114 A
- Clean masonry surfaces by ASTM D4261
- Fill masonry block with AMERLOCK 400 BF block filler or PPG 4-100 acrylic block filler

---

### **Dry wall**

- Tape all joints, fill cracks and nail holes with patching, paste or spackle; sand smooth. Remove all dust. Unsealed drywall will require at least 2 coats of this product

---

### **Substrate temperature and application conditions**

- Surface temperature during application should be between 50°F (10°C) and 130°F (54°C)
- Surface temperature during application should be at least 5°F (3°C) above dew point
- Ambient temperature during application and curing should be between 50°F (10°C) and 100°F (38°C)
- Relative humidity during application should be between 0% and 85%



# PITT-TECH® | 90-374 SERIES

## **Warning**

Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. EXPOSURE TO LEAD DUST OR FUMES MAY CAUSE ADVERSE HEALTH EFFECTS, ESPECIALLY IN CHILDREN OR PREGNANT WOMEN. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted and approved (e.g., NIOSH approved) respirator and proper containment and cleanup. For additional information, contact the USEPA/Lead Information Hotline at 1-800-424-LEAD or the regional Health Canada office

---

## **SYSTEM SPECIFICATION**

- Primers for concrete, masonry, stucco, plaster: 4-603, 4-808, AMERLOCK SERIES (concrete)
  - Primers for CMU: 4-100, AMERLOCK 400BF, 6-15, 16-90
  - Primers for ferrous metal: self priming, 90-712, METALHIDE 2000, 6-208, 7-852
  - Primers for non-ferrous metals: self priming, 90-712, 6-204, 6-208, 6-209
  - Primers for drywall: 6-2, 9-900, 17-921
- 

## **INSTRUCTIONS FOR USE**

- Agitate with a power mixer for 1 – 2 minutes until completely dispersed. Ensure good off-bottom mixing
- 

## **Application**

- Area should be sheltered from airborne particulates and pollutants
- Avoid combustion gases or other sources of carbon dioxide that may promote amine blush and ambering of light colors
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns
- Avoid exterior painting late in the day or when dew or condensation are likely to form or if rain is expected

## **Material temperature**

Material temperature during application should be between 50°F (10°C) and 90°F (32°C)

---

## **Air spray**

- Use standard conventional equipment

## **Recommended thinner**

Tap water

## **Volume of thinner**

0 - 5%

## **Nozzle orifice**

Approx. 0.070 in (1.8 mm)

## **Nozzle pressure**

0.4 - 0.5 MPa (approx. 4 - 5 bar; 55 - 70 p.s.i.)

---



# PITT-TECH® | 90-374 SERIES

**Airless spray**

- 28:1 pump or larger

**Recommended thinner**

Tap water

**Volume of thinner**

0 - 5%

**Nozzle orifice**

0.015 - 0.017 in (approx. 0.38 - 0.43 mm)

**Brush/roller**

- Use a high quality polyester/nylon brush and/or a high quality 3/8" nap roller. In hot or dry conditions, layoff lightly rolling with 3/8" nap roller cover. Multiple coats may be required to achieve specified film thickness

**Recommended thinner**

Tap water

**Volume of thinner**

0 - 5%

**Cleaning solvent**

Soap and water

**ADDITIONAL DATA**

Overcoating interval for DFT up to 2.0 mils (51 µm )				
Overcoating with...	Interval	50°F (10°C)	70°F (21°C)	90°F (32°C)
itself	Minimum	12 hours	5 hours	3 hours
	Maximum	Unlimited	Unlimited	Unlimited

Curing time for DFT up to 2.0 mils (51 µm )		
Substrate temperature	Dry to touch	Dry to handle
50°F (10°C)	2.5 hours	12 hours
70°F (21°C)	70 minutes	5 hours
90°F (32°C)	40 minutes	3 hours



# PITT-TECH® | 90-374 SERIES

## Product Qualifications

- Compliant with USDA Incidental Food Contact Requirements
- Meets MPI Category #154, Interior W.B. Light Industrial Coating, Gloss, MPI Gloss Level 6
- Can help earn LEED 2009 credits
- Performance offset to Federal Standard TT-E-2784

## DISCLAIMER

- For industrial or professional use only

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.



# PITT-TECH® | 90-374 SERIES

## AVAILABILITY

### Packaging

1-gallon and 5-gallon kits

---

Product codes	Description
90-306	Safety Red
90-310	Safety blue
90-311	Safety green
90-313	Safety Orange
90-330	Safety Yellow
90-353	Black
90-374	White and Pastel Base
90-375	Midtone Base*
90-376	Deeptone Base*
90-377	Deep rustic base*

Note: \* Must be tinted

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

