

# Hempaprime Multi 500

## Product characteristics

### Description

Hempaprime Multi 500 is a fast drying, high solids epoxy paint. It provides hard wearing and long lasting barrier protection in coating systems for severe corrosive environments. The product meets the requirements of ISO 12944 Part 5, 2019 when used as part of a predefined paint system.

### Recommended use

Hempaprime Multi 500 is recommended as a high-build, intermediate coat in high performance coating systems where fast handling and short overcoating times are required. Due to its fast drying - up to twice as fast as comparable products - the product is excellent for projects where fast throughput is key. The product can also be used as a self-priming, surface tolerant coat and a finishing coat in heavy-duty coating systems. Suited for application down to 10°C [50°F]. The product is available in several MIO shades such as 18021 and 18061; both with 80% MIO content. The volume solids % for MIO shades is 77 ± 2.

### Service temperature:

- Maximum, dry exposure only: 120°C [248°F].

### Certificates / Approvals

- Meets requirements to ISO 12944 when used as part of a predefined paint system. Part 6, Im2; Part 9, CX.
- Meets requirements to NORSOK M-501 when used as part of a predefined paint system. Edition no. 6, System 1.

### Features

- Fast overcoating.
- Crack resistant in high film thickness.
- Low VOC.
- Ready to use - optimised application properties.
- Surface tolerant.

## Product safety

Flash point 25°C [77°F]

### VOC content mixed product

Legislation	Value
EU	196 g/L [1.64 lb/US gal]
US (coatings)	196 g/L [1.64 lb/US gal]
US (regulatory)	196 g/L [1.64 lb/US gal]
China	196 g/L [1.64 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

## Product data

### Product code

45950

### Product components

Base 45959  
Curing agent 95090

### Standard shade\* / code

Brownish red 50630 \*\*

### Gloss

Semi-gloss

### Volume solids

85 ± 2%

### Specific gravity

1.4 kg/L [12 lb/US gal]

### Reference dry film thickness

150 micron [5.9 mils]

\* Other shades are available, please contact your local Hempel representative.

\*\* Slight discolouration may occur. This does not affect the performance of the coating.

# Hempaprime Multi 500

**Micaceous iron oxide (MIO) shade / code**  
Metallic grey 12430

**Gloss**  
Semi-gloss

**Volume solids**  
85 ± 2%

**Specific gravity**  
1.6 kg/L [14 lb/US gal]

**Reference dry film thickness**  
150 micron [5.9 mils]

## Surface preparation

### Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

### New build:

- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC).
- Remove dust, blast media and loose materials.

### Maintenance and Repair

- Spot abrasive blasting to min. PSa 2 (ISO 8501-2) / SP 6 (SSPC).
- Minor areas may be hand or power tool cleaned instead of abrasive blasting.
- Water jetting to min. Wa 2 (ISO 8501-4).
- Flash rust degree of maximum FR M (ISO 8501-4).
- Remove dust, blast media and loose materials.

### Roughness

- Surface profile Medium (G) (ISO 8503-2).

Consult Hempel's separate Surface Preparation Guidelines for more details.

## Application

### Mixing ratio

Base 45959 : Curing agent 95090  
(4 : 1 by volume)

Stir well before use.

### Thinner

Hempel's Thinner 08450

### Cleaner

Hempel's Tool Cleaner 99610  
Hempel's Thinner 08450

### Pot life

Product temperature	10°C [50°F]	20°C [68°F]	30°C [86°F]
Pot life	2½ hours	1 hour	½ hours

### Application method

Tool	Thinning max vol.	Application parameters
Airless spray	5%	Nozzle pressure: 225 bar [3300 psi] Nozzle orifice: 0.019-0.023"
Brush/Roller	5%	Not Applicable.

Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

### Film thickness

Specification range	Low	High	Recommended
Dry film thickness	100 micron [3.9 mils]	250 micron [10 mils]	150 micron [5.9 mils]
Wet film thickness	120 micron [5 mils]	300 micron [12 mils]	175 micron [7 mils]
Theoretical spreading rate	8.5 m <sup>2</sup> /L [350 sq ft/US gal]	3.4 m <sup>2</sup> /L [140 sq ft/US gal]	5.6 m <sup>2</sup> /L [230 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

# Hempaprime Multi 500

## Application conditions

- Optimal paint temperature for proper mixing, pumping and spraying is: 20°C [68°F].
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Surface temperature must be above 10°C [50°F] during application and curing.

## Application remarks

- Product requires heavy duty spray equipment; spray hoses shall be as short as possible.

## Drying and overcoating

### Product compatibility

- Previous coat: None or according to Hempel's specification.
- Subsequent coat: None or according to Hempel's specification. Recommended products are: Hempadur, Hempaprime, Hemplathane

### Drying time

Surface temperature		10°C [50°F]	20°C [68°F]	30°C [86°F]	40°C [104°F]
Touch dry	hours	2½	1	¾	½
Surface dry	hours	5½	2½	1	½
Hard dry	hours	8	3½	1½	¾

Determined for dry film thickness 150 micron [5.9 mils] at standard conditions, see Hempel's Explanatory Notes for details.

## Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	30°C [86°F]	40°C [104°F]
Atmospheric medium					
Hempaprime Multi 500	Min	7 h	3 h	120 min	90 min
	Max	Ext*	Ext	Ext	Ext
Hemplathane HS 55610	Min	7 h	3 h	120 min	90 min
	Max	Ext*	Ext	Ext	Ext
Atmospheric severe					
Hempaprime Multi 500	Min	7 h	3 h	120 min	90 min
	Max	47 d	21 d	14 d	10 d
Hemplathane HS 55610	Min	7 h	3 h	120 min	90 min
	Max	16 d	7 d	5 d	3½ d

Overcoating times are indicative for products of the same generic chemistry. Consult Hempel's specification for more information.

### Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- According to Hempel's Specification.

### Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

### Other remarks

- Epoxy coats have an inherent tendency of chalking in outdoor exposure. This does not affect the performance of the coating.
- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

# Hempaprime Multi 500

## Storage

### Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Base	24 months	16 months
Curing agent	24 months	16 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

### Storage conditions

- Product must be stored according to local legislation, at maximum 40°C [104°F], without direct sunlight and protected from rain and snow.

## Additional documents

Additional information is available at the Hempel website [hempel.com](http://hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.